

Vacuum Bagging Film

Technical Information

◆ Properties

Color	Yellow
Raw Material	PA+PE+PA
Temperature Resistance	150 °C
Tensile Strength at break	Length direction: >38Mpa Width direction: >35Mpa
Elongation at break	Length direction: >400% Width direction: >400%
Puncture resistance	1.2N

◆ Availability

Thickness	50/ 65/ 75microns
Max width	6.1m
Formats	V sheet, sheet, tube

◆ Storage

Recommended temperature is around 20 °C and relative humidity is around 65%.



NEOTECH COMPOSITE CO., LTD.

บริษัท นีโอสเทค อินสเปกชัน แอนด์ เคมีคัล จำกัด

139 Soi Phrayasuren 30, Phrayasuren rd., Bangchan, Klongsamwa, Bangkok, Thailand 10510. Tel. (662) 5174955-6 Fax (662) 5174957
139 ซอยพระยาสุเรนทร์ 30 ถนนพระยาสุเรนทร์ แขวงบางชัน เขตคลองสามวา กรุงเทพฯ 10510. โทร. 02-5174955-6 โทรสาร 02-5174957