

# Crystic VE 673

## Epoxy Novalac Vinyl Ester Resin

### Introduction

Crystic VE 673 is an epoxy Novolac based vinyl ester resin.

Crystic VE 673 has outstanding chemical resistance to a wide range of substances (strong acids , oxidising agents, chlorinated media and solvents) at room and elevated temperatures.

### Application

Crystic VE 673 is suitable for the fabrication of fibre reinforced composites by all conventional techniques (contact moulding, filament winding, injection moulding) and for use in many chemical processing industry applications (storage tanks, vessels, ducts, scrubbers and chimneys).

### Features and Benefits

Crystic VE 673 has a very high heat distortion temperature giving excellent temperature resistance and superior retention of properties characteristics at higher temperatures.

Crystic VE 673 is resistant to chlorinated media, many solvents and petrol.

### TYPICAL PROPERTIES

Property		Liquid Resin
Acid value	mgKOH/g	7- 11
Viscosity @ 25°C poise (Brookfield RVT)	mPas	250 ± 50*
Density at 20°C	g/ml	1.06 – 1.07
Colour Gardner		max. 7
Volatile content	%	36 ± 2
Shelf life (max 25°C, in the dark)	months	6
Geltime @ 25°C using: [100g resin, 1,0g DMA (10% in Styrene) 0.7g Cobalt Octoate (3%Co) 2.0g Butanox LPT]	minutes	12 – 20*
Time to peak	minutes	18 – 34
Peak exotherm	°C	Min 180

\*Variants available, on request, designed for improved fabrication.

**NB:** LPT catalyst should be used in order to reduce the possibility of foam formation. Alternatively, 1 – 2 % of Trigonox 239 with 0.8 % Cobalt Octoate (3% Co) can be used. If 1% cobalt is available then an addition of 2.4% will be required.

## Mechanical Properties

Properties		Cured cast resin *
Tensile strength **	MPa	75
Tensile modulus**	GPa	3.5
Elongation to break**	%	3
Flexural strength**	MPa	120
Barcol hardness **	-	48
HDT***	°C	125 - 135
Water absorption** : 7 days	mg	60

\*\* Curing Schedule: 24 hrs at 25°C followed by 3 hrs at 80°C.

\*\*\*Curing Schedule: 24 hrs at 25°C followed by 5 hrs at 80°C and then 3 hrs at 120°C.

## Post Curing

Satisfactory laminates for many applications can be made from Crystic VE 673 by curing at ambient temperature (25°C). For optimum properties and long term performance laminates should be post cured before being put into service. The laminate should be allowed to cure for 24 hours at 25°C and then be oven cured for a minimum of 3 hours at 80°C; the time will be dependent upon the thickness of the laminate. Post curing at 100°C is advisable for high operating temperatures.

## Chemical Resistance

Crystic VE 673 has excellent chemical resistance to a wide range of substances; (acids, alkalies, oxidising agents) at room and elevated temperatures and is especially resistant to chlorinated media, many solvents and petrol.

Crystic VE 673 has been tested extensively for its resistance to different kinds of fuel and is ideal for use as an inner liner for fuel storage tanks. After total immersion in both leaded and unleaded fuels for 500 hours at 45°C or 6 months at ambient temperature, Crystic VE 673 based laminates retained over 80% of their flexural properties.

A separate technical leaflet offers the user a comprehensive guide to the use of Crystic VE 673 based laminates in a wide variety of chemical environments.

## Storage

Resin should be stored in dark. It is recommended that storage temperature should be less than 25°C. The storage shelf life of this resin is 6 months when stored in dark below 25 °C.

## Packaging

200 kg resin is supplied in 210 m<sup>3</sup> protected drums, white coloured outside.

## Health & Safety

Please see separate Material Safety Data Sheet.



Scott Bader Middle East Limited  
P.O. Box 16785 Jebel Ali Free Zone, Dubai, U.A.E.  
Telephone: +971-4-8835025, Facsimile: +971-4-8835319  
Email: info@scottbader.co.ae, Website: www.scottbader.com

